

# Nabtesco

## RV OIL SB150

試験項目	試験方法 Test method	RV OIL SB150
基油 Base oil	-----	合成炭化水素油 Synthetic hydrocarbon oil 鉱油 Mineral oil
動粘度(40°C・100°C),mm <sup>2</sup> /s Base oil kinematic viscosity	JIS K 2220 23. ASTM D 445	158(40°C) 19.4(100°C)
粘度指数 Viscosity Index	JIS K 2283	140
外観 Appearance	-----	緑色 Green
引火点,°C Flash point	JIS K 2265-4	260
錆止め性能(60°C,24h) Rust-preventing characteristic	ISO 7120 JIS K 2510	pass
銅板腐食(100°C,3h) Corrosiveness to copper	ISO 2160 JIS K 2513	1a
泡立性(seq-I,24°C),mL/mL Foaming characteristic	ISO 6247 JIS K 2518	0/0
高速四球式耐荷重性能, N Four-ball EP	L.N.S.L. W.P. L.W.I. ASTM D 2783	981 1569 392

注)記載の数値は代表性状値であり、保証値ではありません。

These values are typical properties and we cannot guarantee the applicability of this information in service.

## ナブテスコ株式会社